

Alloy	Similar Powders	Chemical Specification				
Stainless Steel Powders		UNS	ASTM	ISO	AMS	DIN
17-4ph	GP1	17400	A705 S564 A693	15156-3	5604 5643	1.4542
15-5ph	PH1	S15500	A705 S564 A693		5659 5862	1.454
SS 316L	StainlessSteel 316L CL20ES	S31673	F745 F138	5832-1		1.4401 1.4404
SS 304L		S30400			5511 5531 5639	1.4301 1.4307
FeNiCoMo	18Ni30 1.2709					
Rockit 401						

Alloy	Similar Powders	Chemical Specification				
Tool Steel Powders		UNS	ASTM	ISO	AMS	DIN
18Ni300	MS1 CL50WS	K93120			6514	1.2709
H13		T20813	A681		6408	1.2344
P20		T51620	1681			1.2311
Corrax						

Alloy	Similar Powders	Chemical Specification				
Nickel & Cobalt Based Alloy Powder		UNS	ASTM	ISO	AMS	DIN
CoCrMo	MP1 CL111	R31538	F1537 F799 F75	5832-4 5832-12		
CoCrMo	F 75					
Co21		R30021			5819	
HX	NickelAlloy HX	N06002	B 435 B 572		5536 5754 5798	2.4665

Alloy	Similar Powders	Chemical Specification				
Nickel & Cobalt Based Alloy Powder		UNS	ASTM	ISO	AMS	DIN
718	NickelAlloy In718 CL100NB	7718	B537 B670		5832 5596	2. 4668
625	NickelAlloy IN625	6625	446 Gr1 443 Gr1		5599 5666	2. 4856
H188		R3018			5608 5801 5772	2. 4683
		N07214				
		N06230	B435		5878 5891	2. 4733
MK500		N05500	B 865	6208 9723 9725	4676	2. 4375
Ni-SA 738 LC						
Ni-SA 247 LC						
282						

Alloy	Similar Powders	Chemical Specification				
Aluminium Alloy Powders		UNS	ASTM	ISO	AMS	DIN
AlSi10Mg	AlSi10Mg CL31Al	A13600	A03600			3. 2381
AlSi12		A49047				3. 2852

Alloy	Similar Powders	Chemical Specification				
Titanium Alloy Powders		UNS	ASTM	ISO	AMS	DIN
Ti6-4	Titanium Ti64 CL40Ti	R56400	F136 B348 gr 5	5832-3	5954 4911 4928	3. 7164
Ti6-4 ELI	Titanium Ti64ELI CL41Ti-ELI	R56401	F136 B348 gr 23	5832-3	4956	3. 7164

Alloy	Similar Powders	Chemical Specification				
Copper Alloy Powders		UNS	ASTM	ISO	AMS	DIN
GRCop 84						
C18100		C18100				
C18150		C18150				
C18200		C18200				